

PRODUCT SUBMITTAL

WIRE-BOND

Aqua Flash Primer



DESCRIPTION

AQUA FLASH Primer is a solvent/asphaltic base high tack primer specifically designed to promote maximum adhesion of the AQUA FLASH waterproofing membrane on all vertical and horizontal surfaces of concrete, block, brick wood, metal, and gypsum.

APPLICATION INSTRUCTIONS

Substrate surface should be dry, free from oil and grease or any loose debris of any kind. Primer should be stirred in the container and applied either with a soft bristle brush or suitable spray equipment. Allow Primer to dry prior to application of the waterproofing membrane. Dry time is within 24 hrs. A properly applied primer will remain glossy even when dry to the touch. If the primer is not dry, the solvent/moisture trapped beneath the applied membrane could cause the membrane to bubble and lift off of the substrate.

PHYSICAL PROPERTIES:

Weight	8 lbs.
Total solids	62%
Dry time (75°F % @ 50% humidity)	24 Hrs.
Flash Point	100°F Min.
Application Temperature	25°-100° F

SPECIFICATION: Meets ASTM D 41-85, SS-A-701B
Technical Assistance: Telephone 781-461-1946

COVERAGE: 100 square feet/gallon depending on the porosity and condition of the substrate

CLEAN-UP: Wet primer can be cleaned up with, paint thinner or kerosene

Packaging: 5 gallon

Storage

Product should be stored above 40°F. Do not heat container- COMBUSTIBLE.

Product Information: All users of the *AQUA FLASH* products should read the Safety Data Sheets (SDS) which are available from wirebond.com

Corporate Office: 400 Rountree Rd Charlotte, NC 28217
TEL: (800) 849-6722 FAX: (704) 525-3761

Mailing Address: P.O. Box 240988 Charlotte, NC 28224



www.wirebond.com

Memphis Plant: 2365 Harbor Ave. Memphis, TN 38113
TEL: (800) 441-8359 FAX: (901) 775-9449

Mailing Address: P.O. Box 13124 Memphis, TN 38113